



Made in the USA with domestic
and imported ingredients.

POLYMER NATION CHEMICAL COMPANY, LLC

Setting the Standard

847-774-5038 | www.polymernation.com | sales@polymernation.com



405 Oakwood Ave
Waukegan, IL 60085

TECHNICAL DATA SHEET: W-52 CK URETHANE CONCRETE COVE BASE

Product Overview

W-52 CK is a proprietary formulation that allows for longer working time with convenient return to service times. It combines our water-based urethane resin and aromatic hardener with our proprietary blend of Portland cement, lime and fillers (PN 1352-30 CB). It has been formulated to provide the highest degree of impact and thermal shock resistance of any urethane concrete on the market. It's low odor and easy application make it perfect for industrial coving applications.

Uses and Benefits

W-52 CK is primarily used as a cove base around the perimeter base of a room or area. It is used to achieve 1/8"-1/4" thick coving in one pass and can be applied and smoothed with a cove trowel. It can also be applied to green concrete.

Limitations

Each mix of W-52 CK will cover approximately 32 linear ft. (4" cove with 1" radius) at theoretical coverage. A waste factor of 5% should be contemplated when mixing and installing. Ideal application temperatures to be between 60-90°. Cooler temperatures will increase cure times. Warmer temperatures will decrease working and cure times. Verify that substrate temperature is above 5 degrees of dewpoint during application and cure of material to avoid a potential condensation which may lead to adhesion issues.

Surface Preparation

The preparation method for each project is determined by a full understanding of the substrate to be coated, the chemistry of the coating system being used, the coating system thickness, and numerous other factors. The coating installer should fully read and understand ICRI Guideline NO. 310.2R-2013 and OSHA 29 CFR 1926.1153 before starting preparatory work. The aim, of preparing a substrate for coating applications, is to roughen the surface, remove weak layers, contaminants, dirt, debris and present a solid, clean, dry substrate for the primer. If unsure as to the level of preparation needed contact Polymer Nation at Lab@polymerNation.com.

Mixing

A kit consists of 1.05 gal. Part A, 0.75 gal. Part B and 3 - 30 lb. bags of Part C (PN 1352-30 CB); there are **3 mixes per kit** (see *Technical Data* section or chart on Page 2 for individual mix volumes).

Combine part A and B into a single container, large enough to accept an entire mix (1 mix equals ~ 3 gallons when Part C is added). Premix liquids at low speed for 15-30 seconds using an appropriate mixing blade or mixing machine. Add Part C into the mixed resin and continue mixing until a homogenous mortar is achieved (2-3 minutes usually). Do no mix more than can be applied in a 10-15 minute span.

Application

For more details, see **Application** section on Page 2. Recoat within 24 hours. Clean tools with a solvent similar to Denatured Alcohol or Acetone.

Technical Data

The data below was gathered at temperatures of 72-75°F and 30-50% RH

Kit Packaging	1.05 gal. A; 0.75 gal. B; 3 – 30 lb. Bags **Three-mix Kit**
Mix Ratio per mix	Part A - 44.5 oz. Part B - 32 oz. Part C - 30 lbs.
Mixed Viscosity	300 cP 25°C/77°F (A&B)
Working Time	15-20 minutes
Dry to Touch	2-3 hours
Through Dry	4-8 hours
Dry to Light Use	16-24 hours
Full Cure	7 days
Shore D Hardness	D70 @ 24 hours
Shore D Hardness	D78 @ 7 days
Gloss @ 60 Degree Angle	30-50
VOC's of Mixed Material	Near zero <50 g/l EPA Method 24
Color Scale	0.5-1.0 per ASTM D1500
Solids by Volume Mixed	>99%
Application in inches	1/8" – 1/4" (see chart on Page 2)
Available Colors	Natural, Tile Red, Light Gray, Medium Gray, Dark Gray, Black, Tan

W-52 CK Urethane Concrete Cove Base Coverages – 1 Mix

Base

4" Cove with 1" radius (see Note)

6" Cove with 1" radius (see Note)

Linear Feet (+/- 5%)

32 feet (96 ft./kit)

24 feet (72 ft./kit)

W-52 CK Mix

A – 44.5 oz.

B – 32 oz.

C – 30 lbs. PN 1352-30 CB Aggregate

Note: Vertical (non-rounded) portion of cove base was between 1/8" – 1/4" thickness on average

Application: W-52 CK Urethane Concrete Cove Base

Substrate Prep – Prepare the surface to be primed and coved; ensure that the surface is free of contaminants, dirt or loose impediments and that the substrate is profiled to accept a primer.

Primer – Depending on temperature and the desired time between priming and coving, use **SP-71** (medium speed) or **SP-81** (fast speed) polyaspartic to prime the substrate on which **W-52 CK** will be applied. **While the PN polyaspartic primer is still tacky** (before through dry), proceed with application of **W-52 CK**.

Cove Base – Use appropriate tooling (ex: margin trowel, wide putty knife) to apply **W-52 CK** to the cove area; use a cove trowel to smooth and finish the cove base.

C-99 is the preferred material for use as trowel lubricant; using **C-99** in a mist spray bottle either directly to the trowel or directly to the applied cove material is recommended.

PHYSICAL PROPERTIES W-52 CK URETHANE CONCRETE COVE BASE

Description	Standard	Results
Tensile Strength	ASTM C307	1,400 psi
Moisture Absorption	ASTM C413	0.04%
Coefficient of Thermal Lineal Expansion	ASTM C531	2×10^{-5}
Compressive Strength	ASTM C579	8,000 psi
Modulus of Elasticity	ASTM C580	N/A
Flexural Strength	ASTM C580	2,500 psi
Water Vapor Transmission	ASTM D1653	See ASTM D3010
Impact Resistance	ASTM D2794	>160 inch pounds The addition of PC 1244 drastically improves performance
Independent Certificate from third party testing agency	ASTM D3010	Breathable
Adhesion	ASTM D3359	N/A
Abrasion Resistance CS17 1000 g 1000cycles in g Loss	ASTM D4060	0.029g Loss (when higher abrasion resistance is required the addition of PC 1336 to the coating should be included)
Adhesion to Steel	ASTM D4541	N/A
Hiding Power	ASTM D5150	N/A
Flammability When Adhered to Concrete	ASTM D635	Self-Extinguishing
Adhesion to Concrete	ASTM D7234	>450 Substrate failure
Coefficient of Friction Dry Ave. three tests	NFSI B101.0	0.75
Coefficient of Friction Wet Ave. three tests	NFSI B101.1	0.7
Accelerated Weathering Testing	ASTM G154	Significant yellowing

* Dispose of material, containers, solvents, etc., per Federal, State and local guideline, rules and laws.

* Store material between 60-80 degrees F in a protected dry location.

Test data has been gathered from testing conducted by independent, internal and third party testing. The best way to compare coating performance is by head-to-head independent testing as this removes the numerous variables found between testing standards, equipment and testing agencies.

The information here is general information to help our customers determine whether our products suit their specific applications. Our products are intended for sale to commercial and industrial customers. ***We require that customers inspect and test our products before use to satisfy themselves as to the content and suitability for the applications they intend to use our products.*** Nothing herein shall constitute any warranty expressed or implied, including any warranty of merchantability or fitness for a particular purpose, nor is any protection from any law or patent to be inferred. The exclusive remedy for all proven claims is the replacement of our materials, and we shall not be liable for incidental or consequential damages. Polymer Nation Chemical Company LLC, 405 Oakwood Ave. Waukegan, IL 60085. All rights reserved.

Revised: 5/30/25